

Section II. (Amendments to Claims)

Please amend claims 1,

1. (Currently amended) A microelectronic structure comprising:

at least one layer of high dielectric constant material comprising amorphous dielectric metal oxide having: (i) a voltage independent capacitance, (ii) a capacitance density of from about 1000 to about 10,000 nF/cm², and (iii) a current leakage of <10⁻⁷ A/cm²;

at least one conductive barrier layer in contact with the layer of high dielectric constant material, wherein such conductive barrier layer comprises at least one material selected from the group consisting of Pt, Ir, IrO₂, Ir₂O₃, Ru, RuO₂, TaN, NbN, HfN, ZrN, WN, W₂N, TiN, TiSiN, TiAlN, TaSiN, NbAlN, and compatible combinations, mixtures and alloys thereof;

at least one metal layer in contact with the conductive barrier layer, wherein said metal layer comprises metal or metal alloy including a material selected from the group consisting of Cu and Al;

wherein said at least one conductive barrier layer is between said at least one layer of high dielectric constant material and said at least one metal layer;

~~wherein when said material of said at least one metal layer is Al, said at least one material of said conductive barrier layer is not Ir or IrO₂.~~

2. (Currently amended) A microelectronic structure according to claim 1, wherein said conductive barrier layer comprises at least one material selected from the group consisting of TaN, NbN, HfN, ZrN, WN, W₂N, TiN, TiSiN, TiAlN, TaSiN, and NbAlN.
3. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer comprises TiAlN.

4. (Original) A microelectronic structure according to claim 1, wherein said metal layer comprises Cu or Cu alloy.
5. (Original) A microelectronic structure according to claim 1, wherein said metal layer comprises Al or Al alloy.
6. (Currently amended) A microelectronic structure according to claim 1, wherein said ~~layer of high dielectric constant material comprises a complex~~ amorphous dielectric metal oxide is selected from the group consisting of SrBi₂Ta₂O₉ (SBT), (Ba,Sr)TiO₃ (BST), BiTaO₄ (BT), Bi₄Ti₃O₁₂, barium titanate, strontium titanate, barium strontium titanate, strontium bismuth tantalate, bismuth titanate, and lead zirconium titanate and Pb(Zr,Ti)O₃ (PZT).
7. (Currently amended) A microelectronic structure according to claim 1, wherein said layer of high dielectric constant material comprises amorphous SBT perovskite ~~BST~~ material.
8. (Original) A microelectronic structure according to claim 1, wherein said layer of high dielectric constant material comprises amorphous BST material.
9. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer has a thickness in a range of from about 1nm to about 100nm.
10. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer has a thickness in a range of from about 5nm to about 20nm.
11. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer comprises Pt.
12. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer comprises Ir.

13. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer comprises IrO_2 .
14. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer comprises Ru.
15. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer comprises RuO_2 .
16. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer comprises TiAlN.
17. (Original) A microelectronic structure according to claim 1, wherein said conductive barrier layer comprises TaN.
18. (Original) A microelectronic structure according to claim 1, comprising a first conductive barrier layer and a second conductive barrier layer, wherein the first conductive barrier layer is in contact with the layer of high dielectric constant material, and the second conductive barrier layer overlies said first conductive barrier layer and is in contact with the metal layer.
19. (Original) A microelectronic structure according to claim 18, wherein said first conductive barrier layer comprises Pt, and said second conductive barrier layer comprises IrO_2 .
20. (Original) A microelectronic structure according to claim 18, wherein said first conductive barrier layer comprises Pt, and said second conductive barrier layer comprises TiAlN.
21. (Original) A microelectronic structure according to claim 18, wherein said first conductive barrier layer comprises Pt, and said second conductive barrier layer comprises Ir.

22. (Original) A microelectronic structure according to claim 18, wherein said first conductive barrier layer comprises Ir, and said second conductive barrier layer comprises IrO₂.
23. (Original) A microelectronic structure according to claim 18, wherein said first conductive barrier layer comprises Ir, and said second conductive barrier layer comprises TiAlN.
24. (Original) A microelectronic structure according to claim 18, wherein said first conductive barrier layer comprises IrO₂, and said second conductive barrier layer comprises Ir.
25. (Original) A microelectronic structure according to claim 18, wherein said first conductive barrier layer comprises IrO₂, and said second conductive barrier layer comprises TiAlN.
26. (Original) A microelectronic structure according to claim 1, comprising a first conductive barrier layer, a second conductive barrier layer, and a third conductive barrier layer, wherein said first conductive barrier layer is in contact with the layer of high dielectric constant material, said second conductive barrier layer overlies said first conductive barrier layer, and said third conductive barrier layer overlies said second conductive barrier layer and is in contact with the metal layer.

27. (Currently amended) A microelectronic structure comprising:

3A

at least one layer of high dielectric constant material;

~~at least one conductive barrier layer in contact with the layer of high dielectric constant material, wherein such conductive barrier layer comprises at least one material selected from the group consisting of Pt, Ir, IrO₂, Ir₂O₃, Ru, RuO₂, TaN, NbN, HfN, ZrN, WN, W₂N, TiN, TiSiN, TiAlN, TaSiN, NbAlN, and compatible combinations, mixtures and alloys thereof~~ a first conductive barrier layer comprising IrO₂, a second conductive barrier layer comprising Ir₂O₃, and a third conductive barrier layer comprising Ir, wherein said first conductive barrier layer is in contact with the layer of high dielectric constant material, said second conductive barrier

layer overlies said first conductive barrier layer, and said third conductive barrier layer overlies said second conductive barrier layer;

at least one metal layer in contact with the third conductive barrier layer, wherein said metal layer comprises metal or metal alloy including a material selected from the group consisting of Cu or and Al;

wherein said ~~at least one~~ first, second and third conductive barrier layers ~~are~~ layer is between said at least one layer of high dielectric constant material and said at least one metal layer;

~~wherein said at least one conductive barrier layer is between said at least one layer of high dielectric constant material and said at least one metal layer;~~

~~wherein when said material of said at least one metal layer is Al, said at least one material of said conductive barrier layer is not Ir or IrO₂;~~

~~comprising a first conductive barrier layer, a second conductive barrier layer, and a third conductive barrier layer, wherein said first conductive barrier layer is in contact with the layer of high dielectric constant material, said second conductive barrier layer overlies said first conductive barrier layer, and said third conductive barrier layer overlies said second conductive barrier layer and is in contact with the metal layer;~~

~~wherein said first conductive barrier layer comprises IrO₂, said second conductive barrier layer comprises Ir₂O₃, and said third conductive barrier layer comprises Ir.~~

27/28

(Currently amended) A microelectronic structure according to claim 1, comprising:

~~at least one layer of perovskite BST material;~~

a first conductive barrier layer in contact with the ~~layer of perovskite BST material,~~ layer of high dielectric constant material and comprising Pt;

a second conductive barrier layer overlaying said first conductive barrier layer, and comprising Ir; and

~~at least one metal layer in contact with said second conductive barrier layer, comprising Cu or Cu alloy.~~

28 / 29.

(Original) A microelectronic structure according to claim 1, comprising:

at least one layer of amorphous BST material;

a conductive barrier layer in contact with the layer of amorphous BST material, comprising at least one material selected from the group consisting of Ir, Ru, RuO₂, and IrO₂;

at least one metal layer in contact with the conductive barrier layer, comprising Cu or Cu alloy.

29 / 30.

(Original) A microelectronic structure according to claim 1, comprising:

at least one layer of amorphous SBT material;

a conductive barrier layer in contact with the layer of amorphous SBT material, comprising at least one material selected from the group consisting of Ir, Ru, TaN and TiAlN;

at least one metal layer in contact with the conductive barrier layer, comprising Cu or Cu alloy.

30 / 31.

(Currently amended) A microelectronic structure according to claim 1, comprising:

at least one layer of amorphous lead zirconium titanate PZT material;

a conductive barrier layer in contact with the layer of amorphous lead zirconium titanate PZT material, comprising at least one material selected from the group consisting of Ir, Ru, RuO₂, and IrO₂;

at least one metal layer in contact with the conductive barrier layer, comprising Cu or Cu alloy.

~~31~~
32.

(Original) A microelectronic structure according to claim 1, comprising a capacitor structure selected from the group consisting of stack capacitors and trench capacitors.

~~32~~
33.

(Original) A microelectronic structure according to claim 1, comprising a memory cell integrated circuit structure.

~~33~~
34.

(Original) A microelectronic structure according to claim ~~33~~³², wherein the memory cell integrated circuit structure comprises a non-volatile memory cell integrated circuit structure.

~~34~~
35.

(Original) A microelectronic structure according to claim ~~35~~³², wherein the memory cell integrated circuit structure comprises a dynamic random access memory cell integrated circuit structure.

~~35~~
36.

(Original) A microelectronic structure according to claim 1, wherein the integrated circuit structure comprises a decoupling circuit.

~~36~~
37.

(Original) A microelectronic structure according to claim 1, wherein the integrated circuit structure comprises an impedance matching circuit.

~~37~~
38.

(Original) A microelectronic structure according to claim 1, wherein the integrated circuit structure comprises an analog circuit component.

~~38~~
39.

(Original) A microelectronic structure according to claim 1, wherein the integrated circuit structure comprises an active circuit element selected from the group consisting of electrically tunable capacitor, sensor, and microelectromechanical machine (MEMS).

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☒ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.